

gloveon Celeste



Nitrile Exam Gloves Powder Free, Standard Cuff

To don **Celeste** is like putting on a 2nd skin. Its absolute tactility commends it to delicate procedures and jobs plus an assured tensile strength and resistance to chemical expected of a nitrile glove. You owe it to yourself to try this exceptional nitrile glove from **GloveOn**.



| GloveOn Celeste | | |
|------------------------------------|-------------------------|---------------------|
| Length (mm) | ≥ 230 | |
| Thickness Measurements (mm) | | |
| Palm (centre of Palm) | 0.07 ± 0.02 | |
| Finger (13mm ± 3mm from tip) | 0.10 ± 0.02 | |
| Physical Properties | Before Ageing | After Ageing |
| Tensile Strength (MPa) | ≥ 18 | ≥ 16 |
| Elongation (%) | ≥ 500 | ≥ 400 |
| Inspection Levels & AQL | Inspection Level | AQL |
| Watertightness | G1 | 1.50 |
| Physical Dimensions | S2 | 4.00 |
| Tensile Strength | S2 | 4.00 |
| Visual Inspection (Major) | S4 | 2.50 |
| Visual Inspection (Minor) | S4 | 4.00 |
| Particulate Residue | N = 5 | ≤ 2mg/glove |

Chemotherapy Drugs and Concentration
(Tested for Resistance to Permeation by Chemotherapy
Drugs as per ASTM D6978-05-Test Report PN 104145A)

Minimum Breakthrough
Detection Time (minutes)

| | |
|--|--------------|
| Carmustine (BCNU), 3.3mg/ml (3,300 ppm) | 1.2 minutes |
| Cisplatin, 1.0mg/ml (1,000 ppm) | >240 minutes |
| Cyclophosphamide (Cytoxan), 20.0mg/ml (20,000 ppm) | >240 minutes |
| Dacarbazine (DTIC), 10.0mg/ml (10,000 ppm) | >240 minutes |
| Doxorubicin Hydrochloride, 2.0mg/ml (2,000 ppm) | >240 minutes |
| Etoposide (Toposar), 20.00mg/ml (20,000 ppm) | >240 minutes |
| Fluorouracil, 50.0mg/ml (50,000 ppm) | >240 minutes |
| Methotrexate, 25.0mg/ml (25,000 ppm) | >240 minutes |
| Mitomycin C, 0.5mg/ml (500 ppm) | >240 minutes |
| Paclitaxel (Taxol), 6.0mg/ml (6,000 ppm) | >240 minutes |
| Thiotepa, 10.0mg/ml (10,000 ppm) | 30.9 minutes |
| Vincristine Sulfate, 1.0mg/ml (1,000 ppm) | >240 minutes |

WARNING: Carmustine and Thiotepa, at the tested concentration, degraded Celeste nitrile glove at 1.2 minutes and 30.9 minutes, respectively. The safe use of gloves in chemotherapy treatment is solely the decision of clinicians authorised to make such decision.

REORDER CODE

| | |
|---------|---------|
| NTR58XS | X-SMALL |
| NTR58SS | SMALL |
| NTR58MM | MEDIUM |
| NTR58LL | LARGE |
| NTR58XL | X-LARGE |

FEATURES

- Fingertip textured
- Powder free
- Not made with natural rubber latex
- Chemo drugs tested
- Lab chemical tested
- Ambidextrous
- Violet blue colour

PACKAGING

200 gloves per box for XS to L
180 gloves per box for XL
10 boxes per carton

REGULATORY COMPLIANCE

TGA - ARTG 164563, FDA 510(k),
MDD 93/42/EEC, REACH,
ROHS Directive 2002/95/EC,
EC 10/2011,
REGULATION (EC) No 1935/2004,
EC 1935/2004, PPE 89/686/EEC

STANDARDS

ASTM D6319, EN455 part 1, 2, 3 & 4,
EN 1186, EN 13130, CEN/TS 14234,
EN 420, EN 374 part 1, 2 & 3

MANUFACTURING ACCREDITATIONS

ISO 9001:2008
ISO 13485:2003
EN ISO 13485:2003

A brand by

Dmun
www.munglobal.com

Mun USA
Toll free: 888 742 7628
info.us@munglobal.com

gn Protection Always On