

# Heraeus Kulzer

Mitsui Chemicals Group

Pala Lab Putty  
High-precision  
laboratory A-silicone



**PALA**<sup>®</sup>



Fast and precise

Available in two options: 65 and 90 Shore A hardness. Both guarantee fast setting and highly reproducible detail.


Giving a hand to oral health.

# Pala Lab Putty

## High-precision laboratory A-silicone

### Product information:

Pala Lab Putty was developed specifically to provide laboratories with accurate and time saving results. Easy 1:1 mixing guarantees consistency, high fitting accuracy and highly reproducible detail.



### Applications:

- Matrix for:
  - fabrication of hybrid over-dentures
  - construction of provisionals
  - setting anterior teeth in an immediate denture
  - construction of bars
  - processing teeth on a partial denture
- Duplicating models
- Creating preparation models for the repair
- Insulation of teeth against plaster

### Benefits at a glance:

- Easy to mix in 1:1 ratio
- Fast setting time\*
- High reproduction of details (20 µm)
- Dimensional stability over time (<0.05 % after 24 h)
- Heat resistance (e.g. in a pressure curing unit)
- Strong tear resistance
- Can be combined with conventional light-body consistencies

Mixing time	30–45 sec
Working time	1:30 min
Curing time	4:00 min

\*Times from the beginning of mixing at 23°C.

### Delivery forms:

Article. No.	Product name	Shore A hardness	Color	Size
66057432	Pala Lab Putty 90	Shore 90	Light blue	2 x 1.5 kg
66057433	Pala Lab Putty 90	Shore 90	Light blue	2 x 5 kg
66057434	Pala Lab Putty 65	Shore 65	Pink	2 x 1.3 kg
66057435	Pala Lab Putty 65	Shore 65	Pink	2 x 4.5 kg



Contact in Germany  
 Heraeus Kulzer GmbH  
 Grüner Weg 11  
 63450 Hanau  
 Germany  
 info.lab@kulzer-dental.com

Contact in North America  
 Heraeus Kulzer, LLC  
 300 Heraeus Way  
 South Bend, IN 46614-2517  
 customer.servicehkn@  
 kulzer-dental.com  
 www.heraeus-kulzer-us.com